

RenoDeMedici

OVARO



Specifiche Tecniche Technical Specification

Tipo Grade

919

Accoppiato extra liscio

Pasted grey board extra smooth

Stabilimento Mill: Ovaro - Italy

Qualità Quality: GK

Gramm. Substance	Spessore Caliper	Volume Bulk	ISO 2493		ISO 2493		DIN 53121	
ISO 536	ISO 534	ISO 534	g.cm	g.cm	mN.m	mN.m	N.mm	N.mm
g/m ²	mm	cm ³ /g						
1000	1,500	1,50						
1060	1,600	1,50						
1100	1,700	1,50						
1120	1,800	1,60						
1190	1,900	1,60						
1250	2,000	1,60						
1375	2,200	1,60						
1430	2,300	1,60						
1500	2,400	1,60						
1560	2,500	1,60						
1750	2,800	1,60						
1810	2,900	1,60						
1870	3,000	1,60						
2125	3,400	1,60						
2190	3,500	1,60						

Bianco copertina/retro Brightness top/back / ISO 2470 (Photovolt)

Umidità Moisture 7% ISO 287

Tolleranze Tolerances

Grammatura Substance +/- 5% **Media dell'ordine**

Umidità Moisture + 2 / - 1% **Average of order**

Spessore Caliper +/- 3%

Voluminosità Bulk +/- 3%

Rigidità Stiffness /

Grado di bianco Brightness /

Sui singoli campioni (95% dei valori)

For singles determinations (95% of values)

Condizioni ambientali Test Conditions T = 23° C +/- 1 RH = 50% +/- 2

Campionamento Sampling ISO 186

SAHİNLER

Mukavva ve Kağıt Ürünleri San. Tic. A.Ş.

İkitelli O.S.B., Hürriyet Cad.
Saraçlar Sitesi, 14. Blok No:4/1
34490 Başakşehir / İstanbul

Tel : +90 212 485 4575 (pbx)

Fax : +90 212 485 4578

E-mail : info@sahinlerkagit.com.tr